

TEST REPORT

REPORT NUMBER : TURT130077213_REVISED 01
APPLICANT NAME Ceren Kağıt ve Kırtasiye San. A.Ş.
ADDRESS Ziya Gökalp Mah. Eski Turgut Özal Cad. Haseyad İş Merkezi İ.O.S.B Başakşehir / İstanbul
TURKEY
FAX NO :0212 407 06 66
Attention :Berçem Keresteci (bercem@cerenkirtasiye.com.tr)

BUYER NOT GIVEN

SAMPLE DESCRIPTION :
Sample 1 One sample of colour pencil 12 colours / PLAY-KU002
Sample 2 One sample of colour pencil 12 colours tall / PLAY-KU001
Sample 3 One sample of jumbo colour pencil 12 colours / PLAY-KU004
Sample 4 One sample of colour pencil 24 colours / PLAY-KU003
Sample 5 One sample of colour pencil 12 colours in metal box / PLAY-KU006

DATE IN : 22 May, 2013 (09:58)
DATE OUT : 3 June, 2013/15 August,2013
COUNTRY OF ORIGIN: CHINA
ITEM NO: PLAY-KU002 / PLAY-KU001 / PLAY-KU004 / PLAY-KU003 / PLAY-KU006/PLAY-KU005/PLAY-KU007
NOTE: In this revsied 01 report other item no were added.
This report replaces the report no TURT130077213 dated on 03 June,2013 and must be used instead of it.

TEST	Sample 1	Sample 2	Sample 3	Sample 4	Sample 5
SAFETY OF TOYS-PART 1:MECHANICAL AND PHYSICAL PROPERTIES	P (Except 7.1)	X	X	X	X
SAFETY OF TOYS-PART 2:FLAMMABILITY	P	X	X	X	X
SAFETY OF TOYS PART 3:SPECIFICATION FOR MIGRATION OF CERTAIN ELEMENTS	P	P	P	P	P
TOTAL PHTHALATE CONTENT	P	P	P	P	P

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE

The test results relate only to the items tested. The whole and/or the part of this test report shall not be reproduced and shall not be shared with third parties, nor to be used for PR activities without the written permission of INTERTEK Test Hizmetleri A.S.
The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and UKAS accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of UKAS accreditation. Tests marked (*) in this test report are not included in the UKAS accreditation schedule for this laboratory.



Beril SEN
COORDINATOR



Sinan Öncel
CUSTOMER CARE MANAGER



2111

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altındag Plaza Yenibosna 34197 - ISTANBUL / TURKEY
Phone : +90.212. 496 46 46 Fax: +90.212. 452 80 55
e-mail : labtest.turkey@intertek.com
www.intertek-cg-tur.com



130077213

Test Method	Result	Requirements
-------------	--------	--------------

This report details the clauses appropriate to this item. Those clauses not referred to were considered not applicable.

(*)Specification: BS EN 71-1: 2011- Safety of Toys - Specification for Mechanical and Physical Properties

The item was labelled “3+ years”.

The item was tested for children aged over 10 months.

The item was packaging in a cardboard box which was considered to be disposable.

Sample 1

SECTION	TEST	RESULTS
4	General Requirements	
4.1	Material	Pass
4.7	Edges	Pass
4.8	Points & Metallic Wires	Pass
5.10	Small Balls	Pass
7	Warning and Instruction for Use	
7.1	<p>General</p> <p>The toy or, its packaging or document accompanying must be labelled with:</p> <ul style="list-style-type: none"> - The name and address of the manufacturer.** - A CE mark in the correct size. - Warning and other information should be in the national language(s) of the countries where the toy is marketed. <p>**In the case of the toy sell in European countries, the toy, its packaging or document accompanying must be labelled with the name and address of the manufacturer and importer.</p> <p>The importer name is not clearly pointed out as importer It’s recommended to be identified with the title of ‘importer’.</p>	See Comment



Test Method	Result	Requirements
-------------	--------	--------------

(*)Specification: BS EN 71-2: 2011 Safety of Toys – Flammability

Sample 1

SECTION	TEST	RESULTS
4.1	General	
	Celluloid/cellulose nitrate and materials with a same burning behaviour in fire	Pass



2111

Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5

1- Composite sample of yellow, white, orange outer part

	<u>RESULT IN ppm</u>	<u>PASS/FAIL</u>	<u>Requirement (ppm)</u>
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

2- Composite sample of yellow, white, orange tip

Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



2111

Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5

3- Composite sample of neon pink, yellow, salmon tip

	<u>RESULT IN ppm</u>	<u>PASS/FAIL</u>	<u>Requirement (ppm)</u>
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

4- Composite sample of neon pink, yellow, salmon outer part

Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5	RESULT IN ppm	PASS/FAIL	Requirement (ppm)
5- Composite sample of purple, indigo, royal outer part			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500
6- Composite sample of purple, indigo, royal tip			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5	RESULT IN ppm	PASS/FAIL	Requirement (ppm)
7- Composite sample of green, petrol, mint outer part			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500
8- Composite sample of green, petrol, mint tip			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5	RESULT IN ppm	PASS/FAIL	Requirement (ppm)
9- Composite sample of red, blue, light green outer part			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500
10- Composite sample of red, blue, light green tip			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5	RESULT IN ppm	PASS/FAIL	Requirement (ppm)
11- Composite sample of grey, beige, pim outer part			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500
12- Composite sample of grey, beige, pim tip			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5

	<u>RESULT IN ppm</u>	<u>PASS/FAIL</u>	<u>Requirement (ppm)</u>
13- Composite sample of brown, bordeaux, light brown outer part			
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

14- Composite sample of brown, bordeaux, light brown tip

Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5

15- Composite sample of black, emerland outer part

	<u>RESULT IN ppm</u>	<u>PASS/FAIL</u>	<u>Requirement (ppm)</u>
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

16- Composite sample of black, emerland tip

Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



2111

Test Method	Result	Requirements
-------------	--------	--------------

Safety of toys. Specification for Migration of Certain Elements

BS EN 71-3 : 1995

Acid extraction method was used and toxic elements content were determined by Inductively Coupled Plasma-ICP_OES.

Sample 1&2&3&4&5

17- Multicolor metal box

	<u>RESULT IN ppm</u>	<u>PASS/FAIL</u>	<u>Requirement (ppm)</u>
Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

18- Transparent plastic cover

Antimony (Sb)	<2 ppm	PASS	60
Arsenic (As)	<2 ppm	PASS	25
Barium (Ba)	<2 ppm	PASS	1000
Cadmium (Cd)	<2 ppm	PASS	75
Chromium (Cr)	<5 ppm	PASS	60
Lead (Pb)	<5 ppm	PASS	90
Mercury (Hg)	<2 ppm	PASS	60
Selenium (Se)	<2 ppm	PASS	500

ppm (part per million) =mg / kg
 < =Less Than

(Estimated Total uncertainty=Results quoted have been corrected for uncertainty. -)



2111

Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

1- Composite sample of yellow, white, orange, neon pink, yellow outer part	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

2- Composite sample of yellow, white, orange, neon pink, yellow tip	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

3- Composite sample of salmon, purple, indigo, royal, green outer part	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

4- Composite sample of salmon, purple, indigo, royal, green tip	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

5- Composite sample of petrol, mint, blue, red, light green outer part	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

6- Composite sample of petrol, mint, blue, red, light green tip	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

7- Composite sample of grey, beige, pink, brown, bordeaux outer part	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004

Sample 1&2&3&4&5

8- Composite sample of grey, beige, pink, brown, bordeaux tip	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

9- Composite sample of light brown, black, emerland outer part	
	<u>RESULT (%, w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%, w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
-------------	--------	--------------

TOTAL PHTHALATE CONTENT

EN14372 :2004 Method By Gas Chromatographic- Mass Spectrometric (GC- MS) Analysis : 2004
Sample 1&2&3&4&5

10- Composite sample of light brown, black, emerland tip	
	<u>RESULT (%. w/w)</u>
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	ND
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)
	<u>RESULT (%. w/w)</u>
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0,1% (1000 ppm)

REMARK =The Above Limit Was Quoted According To Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content.
 =Correction of the mass due to untreated textile components has been done

ppm (part per million) =mg / kg
 Detection Limit = DINP, DIDP: 100 ppm, Other phthalates: 10 ppm
 < =Less Than
 * =EXCEEDED LIMIT
 ND =Not Detected

COMMENT =The Phthalate Content Test Result DID NOT EXCEED The Limit Of 0.1% By Weight As Stated In European Commission Directive 2005/84/EC On 14 December 2005 Relating To Restrictions On Phthalates In Toys And Children Articles.

(Estimated Total uncertainty=± 5 %)



Test Method	Result	Requirements
		
		

Test Method	Result	Requirements
-------------	--------	--------------



END OF TEST REPORT